

## Viking Torch-On

Version: 1.0

### Concrete

Date Started	
Approved Applicator Company	
Viking Licenced Installer	
Project Name & Address	
Main Contractor	
Membrane Type	
Add any notes or comments:	

- ☐ Ensure concrete substrate has been allowed to fully cure – at least 28 days from pour.
- ☐ If the concrete is less than 28 days old or a rapid curing compound has been used, you must identify the product and verify correct curing has taken place prior to laying.
- ☐ Relative humidity/moisture content of concrete substrates must be no more than 75% before application. This can be verified with the use of hygrometer), \*if moisture level is high use the Viking Roofspect Vented Base Sheet (SEM701)  
\*Venting installed as required. Contact Viking Roofspect if a venting specification has not been provided.
- ☐ Fill hollows or holes with a cement plaster, or FLC within limitations of product used.
- ☐ Surface to be steel trowel finished smooth, without nibs or voids, clean, dry and free of debris or release agents.
- ☐ Minimum 20mm bitumen fillets required at the base of upstands for Torch-On Membrane
- ☐ All drains and outlets are membrane compatible. Confirm with Viking Roofspect if required.
- ☐ Ensure consented falls are met. Refer Viking Membrane BRANZ Appraisal and project specification.
- ☐ Minimum 20mm triangular fillets required at the base of upstands for Torch-on.
- ☐ Viking recommend Viking Licenced Installer applies Viking Bitumen Fillet
- ☐ Please ensure you have ordered the correct membrane, colour and thickness for your project

July 2023

## SUBSTRATE CHECKLIST

### NOTES:

- Cover the substrate to keep it dry, ensuring the waterproofing membrane can be installed when needed. Communicate early with your Viking Approved Applicator on the project scheduling to ensure weather exposure is kept to a minimum.
- Correct substrate installation is critical to durability and performance of the membrane. Failure to strictly comply with substrate specification may affect product warranty.
- All constructions should comply with the New Zealand Building Code. Contact your local council for further advice.
- Communication between the Applicator and Construction Company will assist to ensure specification is met.

Information regarding our products, specifications and warranties is available at [www.vikingroofs spec.co.nz](http://www.vikingroofs spec.co.nz) If you have a query regarding this substrate specification, please call Viking on 0800 729 799

#### Auckland office

80 Alexander Crescent,  
Otara PO Box 14-541,  
Panmure, Auckland  
1741, New Zealand

#### Christchurch office

2 Nazareth Avenue,  
Middleton, PO Box  
9117, Tower Junction  
Christchurch 8149,  
New Zealand

#### Wellington office

19 Pretoria St,  
Lower Hutt 5010,  
New Zealand

T: 0800 729 799

F: 0800 729 788

[info@vikingroofs spec.co.nz](mailto:info@vikingroofs spec.co.nz)  
[www.vikingroofs spec.co.nz](http://www.vikingroofs spec.co.nz)

A division of Viking Group Limited